

NEW BUILD: BUILDING WITH NHL 5

Block work (Building)

Dosages 1 (30 Kg) bag of NHL 5 to 86 litres of sand OR 1:2

For the above joint sizes have been assumed to be 10mm

Sands: 3mm down to 0.075, sharp/well graded. A small proportion of larger aggregates can be used for aesthetical reasons if it is wished to expose them.

Always wet or dampen the bricks or blocks to control suction.

Brushing: to expose the aggregate brushing can be applied after a firm setting (approx. 12/24 hours)

NEW BUILD AND (Exterior) POINTING WITH NHL 3.5

Rebuilding and Pointing Stonework

1. Dosages (for very well graded grit sand) 1 (25Kg) bag of NHL 3.5 to 100 litres of sand OR 1:2.5

2. Dosages (for well graded sand) 1 (25Kg) bag of NHL 3.5 to 83 litres of sand OR 1:2

For the above joint sizes have been assumed to be 10mm

Sands: 3mm down to 0.075, sharp/well graded. A small proportion of larger aggregates can be used for aesthetical reasons if it is wished to expose them.

Always wet or dampen the bricks or blocks to control suction.

Brushing: to expose the aggregate brushing can be applied after a firm setting (approx. 12/48 hours)

All the above information is given as general indication only. Dosages may vary in accordance to materials and aggregates used and site conditions. If you have any questions or queries please do not hesitate to contact Womersley's Limited on Tel 01924 400651 or call in at our workshop.